

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
4 September 2003 (04.09.2003)

PCT

(10) International Publication Number
WO 03/073530 A2

(51) International Patent Classification?: **H01M**

(21) International Application Number: PCT/US03/05895

(22) International Filing Date: 27 February 2003 (27.02.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
10/090,137 27 February 2002 (27.02.2002) US

(71) Applicant: **RAYOVAC CORPORATION** [US/US]; 601 Rayovac Drive, Madison, WI 53744-4960 (US).

(72) Inventors: **ARMACANQUI, Miguel, E.**; 4322 Critchell Terrace, Madison, WI 53711 (US). **NDZEBET, Ernest**; 8501 Old Sauk Road, Apt. 228, Middleton, WI 53562 (US). **BUSHONG, William, C.**; 6306 Keelson Drive, Madison, WI 53705 (US). **MOY, Gregory, S.**; 5301 Shawano Terrace, Madison, WI 53705 (US). **VU, Viet, H.**; 3926 Meridian Circle, Verona, WI 53593 (US). **MIHARA,**

David, R.; 5 San Antonio Court, Madison, WI 53719 (US). **POIRIER, Jeffrey, A.**; 225 Carillon Drive, Madison, WI 53705 (US).


(74) Agent: **FORMAN, Adam, J.**; Quarles & Brady LLP, 411 East Wisconsin Avenue, Milwaukee, WI 53202 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: ALKALINE CELL WITH PERFORMANCE ENHANCING ADDITIVES



(57) Abstract: A sulfonic acid type organic surfactant is incorporated into the gelled anode mixture of an alkaline electrochemical cell, optionally with an organic phosphate ester surfactant. Zinc fines may also be incorporated into the anode. The electrolyte included in the anode mixture may have a reduced hydroxide concentration. When a cell is provided whose anode mixture includes the two surfactants and zinc fines alone or in combination with a lowered hydroxide concentration in the electrolyte, discharge leakage is reduced and gel gassing is suppressed relative to that of gels lacking both surfactants. Additionally, cell discharge performance is improved relative to that of cells lacking both the zinc fines and lowered hydroxide concentration.

WO 03/073530 A2

WO 03/073530 A2



Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

ALKALINE CELL WITH PERFORMANCE ENHANCING ADDITIVES

CROSS-REFERENCE TO RELATED APPLICATIONS

[0001] This is a continuation-in-part of USSN 10/090,137, filed February 27, 2002 and entitled "Alkaline Cell with Gassing Inhibitors", the disclosure of which is hereby incorporated by reference as if set forth in its entirety herein.

STATEMENT REGARDING FEDERALLY
SPONSORED RESEARCH OR DEVELOPMENT

[0002] Not yet determined.

BACKGROUND OF THE INVENTION

[0003] Zinc anode gels of alkaline electrochemical cells are prone to electrochemical corrosion reactions when stored at or above room temperature. The alkaline electrolyte in the anode gel corrodes the zinc anode upon contact, forming oxidized zinc products that decrease the availability of active zinc while simultaneously generating hydrogen gas. The rate of corrosion tends to increase as the electrolyte is made more diluted and as the storage temperature rises and can lead to a significant decrease in cell capacity. Cell discharge performance, on the other hand, can be improved making the electrolyte increasingly diluted. It is thus desirable to suppress gas generation when using diluted alkaline electrolytes for increased performance. The additional water aids in the following cathodic reaction:



[0005] However, lowering the hydroxide concentration in the electrolyte can cause the anode to become over-diluted and depleted in hydroxide ions which are needed to sustain the anodic cell reaction:



[0007] The depletion of hydroxide ions can become prominent during medium and high continuous discharge rates and induce depressed cell performance due to anode failure in these

cases. Furthermore, when the electrolyte is saturated with zincate $\text{Zn}(\text{OH})_4^{2-}$ produced in the above reaction, the zincate precipitates to form zinc oxide which, in turn, passivates the zinc anode, thereby lowering cell performance.

[0008] Additionally, hydrogen gas generated during corrosion reactions can increase the internal cell pressure, cause electrolyte leakage and disrupt cell integrity. The rate at which the hydrogen gas is generated at the anode zinc surface accelerates when the battery is partially discharged, thereby decreasing the battery's resistance to electrolyte leakage. The electrochemical corrosion reactions that lead to hydrogen evolution involve cathodic and anodic sites on the zinc anode surface. Such sites can include surface and bulk metal impurities, surface lattice features, grain boundary features, lattice defects, point defects, and inclusions.

[0009] To minimize undesirable corrosion and gassing during storage, it is typical to employ corrosion-resistant zinc alloys and to reduce the extent of impurities in the anode. Additionally, organic surfactants and inorganic corrosion-inhibiting agents are commonly added to zinc anodes. Surfactants act at the anode-electrolyte interface by forming a hydrophobic film that protects the zinc anode surface during storage. The inhibitive efficiency of surfactants to increase the corrosion resistance of zinc depends on their chemical structure, concentration, and their stability in the electrolyte.

[0010] Among the surfactants known to be effective at controlling gassing are organic phosphate esters such as the ethylene oxide-adduct type disclosed by Rossler et al. in U.S. Patent No. 4,195,120, incorporated herein by reference. In U.S. Patent No. 4,777,100, Chalilpoyil et al. disclosed an anode containing single crystal zinc particles with a surface-active heteropolar ethylene oxide additive including organic phosphate esters. In U.S. Patent No 5,378,559, Randell et al. disclose a galvanic cell that contains a phosphate ester compound to reduce gassing attributed to the brass anode current collector.

[0011] Despite their ability to control gel gassing and cell gassing, organic phosphate ester corrosion-inhibiting surfactants also typically decrease high rate discharge performance in electrochemical cells and can adversely affect intermittent cell discharge performance. Therefore, new approaches are sought for inhibiting corrosion and preventing leakage without simultaneously reducing high rate cell discharge performance. At the same time, it is also of interest to develop new classes of corrosion-inhibiting surfactants for use in gelled anodes of alkaline electrochemical cells.

BRIEF SUMMARY OF THE INVENTION

[0012] The present invention is summarized in that acceptable gel gassing levels are maintained when the gel of an alkaline electrochemical cell contains a surfactant having the general formula $Y SO_x^-$ where preferably $x = 3$ or $x = 4$ and Y preferably is selected from an alkyl group, an aryl group, an alkylaryl group, and a carboxy sulfonic acid group $[(CH_2)_n-COO^-]$, or a salt of any of the foregoing, where the number of carbon atoms, n , in an alkyl chain preferably ranges from 1 to about 26. To the knowledge of the inventors, sulfonated or sulfated acid type surfactants have not previously been employed in gelled anodes, but are shown herein to effectively help inhibit discharge leakage and to maintain cell integrity.

[0013] The invention is further summarized in that unexpected and advantageous benefits are recognized when the aforementioned acid type surfactant or salt thereof is used in combination with a phosphate ester surfactant that can be added to the gelled anode in an amount ranging from 0.0003% to .02%. For example, cell reliability can be maintained and cell gassing can be suppressed.

[0014] The invention is further summarized in that unexpected and advantageous benefits are recognized when the aforementioned acid type surfactant or salt thereof is used in combination with a phosphate ester surfactant when zinc particles are added to the gelled anode. For example, cell performance can be increased and cell gassing can be suppressed.

[0015] The invention is further summarized in that unexpected and advantageous benefits are recognized when the aforementioned acid type surfactant or salt thereof is used in combination with a phosphate ester surfactant when the gel contains an electrolyte having a hydroxide concentration less than 40%. For example, cell performance can be increased and cell gassing can be suppressed.

[0016] It is an object of the present invention to provide an alkaline electrochemical cell in combination with either or both of zinc particles added to the anode, and an electrolyte having a hydroxide concentration less than 40%.

[0017] It is a further object of the present invention to provide a class of surfactants for reducing gelled anode gassing in an alkaline electrochemical cell in combination with either or both of zinc particles added to the anode, and an electrolyte having a hydroxide concentration less than 40%.

[0018] It is an advantage of the present invention that, when zinc particles are added to the gelled anode mix, gel gassing is controlled in an alkaline electrochemical cell that includes a sulfonic acid type surfactant in the gelled anode mix.

[0019] It is another advantage of the present invention that gel gassing is controlled and cell discharge performance is increased in an alkaline electrochemical cell that includes both a sulfonated or sulfated organic acid type organic surfactant, an organic phosphate ester surfactant, and an electrolyte having a hydroxide concentration less than 40% in the gelled anode mix.

[0020] These and other aspects of the invention are not intended to define the scope of the invention for which purpose claims are provided. In the following description, reference is made to the accompanying drawings, which form a part hereof, and in which there is shown by way of illustration, and not limitation, a preferred embodiment of the invention. Such embodiment does not define the scope of the invention and reference must be made therefore to the claims for this purpose.

BRIEF DESCRIPTION OF THE SEVERAL VIEWS OF THE DRAWINGS

[0021] The following figures are presented, in which:

[0022] Fig. 1A is a graph illustrating levels of gassing in an electrochemical cell having varying amounts of Witconate and RM-510 added to its gelled anode mixture;

[0023] Fig. 1B is a graph illustrating the performance of an electrochemical cell having varying amounts of Witconate and RM-510 added to its gelled anode mixture;

[0024] Fig. 1C is a graph illustrating the performance of an electrochemical cell having various inhibitors added to its gelled anode mixture;

[0025] Fig. 2 is a 3-dimensional representation of cell longevity as a function of KOH concentration in the electrolyte and the amount of inhibitor added to the anode;

[0026] Fig. 3 is a graph illustrating the effect of the addition of RM-510 and Witconate to the anode of a cell on cell performance;

[0027] Fig. 4 is a graph illustrating the effect of the addition of RM-510, Witconate, and zinc fines to the anode of a cell on cell performance;

[0028] Fig. 5 is a graph illustrating cell performance as a function of the concentration of zinc fines in the anode; and

[0029] Fig. 6 is a graph illustrating cell performance as a function of the hydroxide concentration of electrolyte used to pre-wet the separator; and

[0030] Fig. 7 is a graph illustrating cell performance of a function of a mix of inhibitors added to the anode.

DETAILED DESCRIPTION OF THE INVENTION

[0031] The present invention relates to the use of a sulfonated or sulfated organic acid surfactant alone or in combination with an organic phosphate ester surfactant. In the present invention, the inhibitor(s) are added into the gelled anode of an alkaline electrochemical cell. The invention further contemplates that the amount of electrolyte present may be reduced, and zinc fine particles (also referred to herein as zinc fines) may be added to the electrolyte, either alone or in combination with each other, and alone or in combination with the inhibitor(s) described herein (e.g., phosphate surfactant and/or sulfonated organic surfactant) to produce improved cell performance.

[0032] A gelled anode mixture, a gelled anode, and an electrochemical cell containing the gelled anode can have the structures of and can be prepared as described in US Patent No. 6,040,088, incorporated by reference herein as if set for in its entirety, except as detailed below.

[0033] A suitable gelled anode according to the invention comprises a metal alloy powder (preferably an alloyed zinc powder), a gelling agent and an alkaline electrolyte. The skilled artisan can readily select a suitable zinc alloy powder and an alkaline electrolyte from those known to the art. It is noted that known gelling agents other than the sodium polyacrylate gelling agent described in the incorporated patent are suitable for use in the present invention. Such gelling agents include carboxymethyl cellulose, crosslinking-typed branched polyacrylate acid, natural gum, and the like.

[0034] A preferred sulfonated or sulfated organic acid type organic surfactant has the general formula $Y SO_x^-$ where preferably $x = 3$ or $x = 4$ and Y is preferably selected from an alkyl group, an aryl group, and alkylaryl group, and an carboxy acid group $[(CH_2)_n-COO^-]$, or a salt of any of the foregoing, where the number of carbon atoms, n , in an alkyl chain ranges from 1 to about 26. Among these surfactants, octadecanoic acids, such as oleic acid, and salts thereof are preferred. A

particularly preferred agent is a sodium salt of sulfated oleic acid commercially available under the trade name Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV. Other suitable sulfonated aryl, alkyl aryl, or alkyl compounds include other Witconate surfactants such as Witconate 90FH, Witconate 93S, Witconate 605A, and Witconate 1260.

[0035] The sulfated organic acid type surfactant is advantageously provided in the gelled anode mix at a concentration ranging from between about 0.001% to about 0.06% relative to the weight of the gelled anode (10 ppm and 600 ppm), and more preferably between about 0.002% and about 0.03% (20 ppm and 300 ppm). In the stated ranges, the sulfonated organic surfactant, alone or in combination with an organic phosphate ester surfactant, reduced KOH concentrations and zinc fines added to the anode, provides desirable gel characteristics as described herein. In the stated ranges, and in the presence of a phosphate organic ester, the sulfonated organic surfactant tends to suppress overdischarge leakage while reducing gel gassing and improving on intermittent discharge performance. Overdischarge leakage is reduced by at least 20%, more preferably by at least 50%, and most preferably to 0, relative to cells lacking these surfactants. When an organic phosphate ester surfactant is provided in the gelled anode mix, it is present at a concentration ranging from between about .0003% and about .02% relative to the weight of the gelled anode (3ppm and 200 ppm), and more preferably between about .0003% and about .005% (3 ppm and 50 ppm).

[0036] The invention further contemplates that the amount of inhibitor added to the cell may be expressed as a function of the weight of metal (e.g., zinc) in the anode. In particular, RM-510 is preferably added in the range of .0004% to .015% relative to the weight of metal in the gelled anode, and more preferably between .0004% and .0075%. Witconate is preferably added in the range of .0015% and .09% relative to the weight of metal in the gelled anode, and more preferably within the range of .003% and .045%. Either or both inhibitor may be added to the gelled anode mix either alone or in combination in accordance with any of the embodiments described in this disclosure, unless otherwise specified.

EXAMPLES

[0037] Table 1 shows that the three-day gassing rate of gels containing the sulfonated surfactant and the phosphate ester in combination was appreciably suppressed relative to that of surfactant-free gels or to that of gels containing either surfactant alone. The gels of Table 1 were

supplemented as shown either with RM-510 to 0.0035%, with Witconate 1840X to 0.0125%, or with both surfactants at the same concentrations, relative to the weight of zinc in the anode gel.

Table 1

Description of Gel sample	Three-day Gel Gassing
	$\mu\text{l/g/day}$
No inhibitor	6.2 ± 1.0
RM-510	5.4 ± 0.9
Witconate 1840X	6.8 ± 0.6
Witconate 1840X + RM-510	3.9 ± 0.5

[0038] Table 2 summarizes partial discharge cell gassing measured in LR03 cells after discharge at 7.5 ohm to a 1.0 volt end voltage and storage for two weeks at 160°F. Overdischarge leakage was measured after continuous discharge at 10 ohms for 48 hours followed by room temperature storage for five weeks. Discharge performance of LR03 cells at 600 mA during 10 seconds per minute for 1 hour a day, was improved over the discharge performance of cells containing the phosphate ester alone. The gelled anode of otherwise conventional alkaline LR03 cells contained RM-510 to about 0.0035% either alone or in combination with Witconate 1840X to about 0.0125%, the amount of both surfactants being measured relative to the weight of zinc alloy in the anode.

Table 2

	Overdischarge Leakage %	Partial Discharge Cell Gas MI	600 mA Pulse No-delay Cycles to 0.9V
Witconate + RM-510	20	0.36 ± 0.11	390.4 ± 3.5
RM-510	60	0.50 ± 0.23	362.2 ± 13.8

[0039] Further, Table 3 shows that the discharge performance at 500 mA of continuous discharge of the LR03 cells containing both surfactants in the gelled anode was superior to that of the cells that contained only the phosphate ester additive. Table 3 also shows that the high-rate constant current discharge performance after high temperature storage was significantly better in the LR03 cells containing both surfactants than in cells containing the phosphate ester alone.

Table 3

500 mA No-Delay Minutes to 0.9 V	500 mA 14 days at 130 °F Minutes to 0.9 V
--	---

Witconate + RM-510	52.6 ± 2.8	55.6 ± 1.7
RM-510	48.0 ± 0.9	53.0 ± 1.7

[0040] Electrochemical cells described herein are generally of the type having a positive current collector, and a cathode in contact with the positive current collector. The cell includes a gelled anode including at least a metal alloy powder (which could be a zinc alloy powder), a gelling agent, and an alkaline electrolyte. A separator is disposed between the cathode and the anode, and a negative current collector is in electrical contact with the anode.

[0041] Fig. 1A illustrates the gassing characteristics of a LR6 electrochemical cell (size AA) having various amounts of Witconate in combination with RM-510. The results indicate that anode gel gassing is reduced as Witconate is increasingly added to the anode. Fig. 1B illustrates the performance of the cell tested corresponding to data shown in Fig. 1A, and indicates that cell performance increases until reaching an optimal value before decreasing. Under the parameters of this test, a Witconate concentration of 125 ppm relative to the gelled anode mixture achieved optimal results, though any amount of Witconate present in the anode between 0 and 209 ppm increased cell performance compared to the control cell that was inhibitor free. Fig. 1C illustrates that the addition of Witconate and RM-510 in the anode of an electrochemical cell enables increased cell performance at 1 A of continuous discharge over a cell containing RM-510 alone, or a cell that is inhibitor free. The performance was measured using the amount of time needed for the cell to output 1 volt during discharge at 1 A.

[0042] It should be appreciated that electrochemical cells may be tested in accordance with several methods under the American National Standards Institute (ANSI). These tests include determining cell performance/longevity under situations of constant cell discharge, cell pulse discharge (i.e., repeated application of 1 A for a period of 10 seconds carried out every minute over the period of an hour per day), and intermittent cell discharge (i.e., a continuous discharge for repeated limited periods of time, for example one hour per day). The present invention recognizes that the various embodiments of the present invention increase cell performance under one or more of these tests, as will now be described.

[0043] For instance, Fig. 2 illustrates the ANSI results of a LR6 cell including zinc fines and RM-510 inhibitor that was tested at 3.9 Ohm 1Hr/day of discharge. In particular, the life of the cell is measured under various conditions of KOH concentration (measured as a percentage by weight of total electrolyte, i.e., the KOH concentration) and under various amounts of RM-510 added to the anode. It is observed that the service life of the cell is increased as the concentration of KOH in

the electrolyte is decreased from 38% to 33%, which reduces anode passivation. The present invention recognizes that advantages may be achieved in a cell whose electrolyte has a concentration of 30% to 40%. Furthermore, as is discussed in more detail below, cell performance may be enhanced using an anode gel having a KOH concentration between 20% and 30%. It is further observed that, while the addition of RM-510 alone is known to suppress gassing in the cell, overall cell performance is reduced as additional RM-510 is added. Nevertheless, the suppression of gassing is desirable to reduce the risk of increased internal cell pressure, which could cause electrolyte leakage and disrupt cell integrity.

[0044] Referring to Fig. 3 the performance of a LR6 cell having a KOH concentration of 34% and RM-510 and Witconate added to the cell anode was compared to a control cell having a KOH concentration of 34% and RM510 added to the anode. The cells were discharged at several constant current rates. The results indicate that reduction of KOH concentration in the electrolyte, and the addition of RM-510 and Witconate to the anode increases cell performance compared to conventional cells. Performance was determined based on the amount of time needed for the cell to reach a discharge voltage of .8V at 2.2 and 3.9 ohm, and .9 V at 250 mA and 500 mA.

[0045] The present invention recognizes that another factor that controls cell performance relates to the surface area of the anode. Specifically, increasing the active anode electrode surface area provides sufficient active reaction sites needed to keep up with the cathodic reaction at high discharge rates. Accordingly, cells are provided having a predetermined amount of zinc particles (which may either be in the form of zinc or a zinc alloy) added to the anode gel. The present invention contemplates zinc particles less than about 75 microns (-200 mesh size), that is, particles that pass a 200 mesh screen size are present in the anode in an amount less than approximately 10%, by weight relative to the total zinc in the anode (including coarse zinc particles), and preferably within the range of 1% and 10%, and more preferably between the range of 1% and 8%, and more preferably still within the range of 4% and 8%, it being appreciated that smaller particles further increase the effective surface area of the anode. Mesh sizes are stated herein to specify a range of particle sizes. For example, -200 mesh indicates particles smaller than 75 microns, while +200 mesh indicates particles larger than 75 microns. Alternatively still, desirable results may be attained using an amount of zinc fines greater than 10%, while the zinc particles having a diameter between 75 and 105 microns (+75 and -140 mesh size) may be present at anywhere between 1% and 50%, and more preferably between 10% and 40%, by weight of total zinc present in the anode.

[0046] The present invention recognizes that multiple ranges of zinc particles having a diameter less than 105 microns (-140 mesh size) including particles between 75 and 105 microns (+200 and -140 mesh size) and zinc fines less than 75 microns (-200 mesh size), may be used to increase cell performance. For instance, it has been discovered the anode may include zinc particles between 75 and 105 micrometers, and that the advantages in cell performance are enhanced when the anode gel has an electrolyte (KOH) concentration less than 30%, and preferably between 20% and 30%. When zinc fines have a size between the range of 20 and 75 micrometers (+625 and -200 mesh size), and preferably between 38 and 75 micrometers (+400 and -200 mesh size), cell performance is particularly enhanced when the KOH concentration is between 30% and 40%, and preferably between 33% and 38%. Yet another preferred range within the range of 20% and 40% KOH concentration is the range between 20% and 34%, and more preferably 25% and 33%, and more preferably still between 25% and 30%. A "low KOH concentration" as used in this disclosure refers to a KOH concentration within any of the above-stated ranges.

[0047] Even though improved cell performance has been correlated to the preferred ranges of zinc fine sizes in combination with the low KOH concentrations, one skilled in the art would also recognize the benefits of the addition of zinc fines and reduction of KOH individually. Accordingly, the present invention includes within its scope the addition of zinc fines to an anode gel having a size within any of the above-stated ranges either individually or in combination with any of the above-stated KOH concentrations. Likewise, the present invention includes within its scope an anode gel having a KOH concentration within any of the above-stated ranges either individually or in combination with zinc fines having a size within any of the above-stated ranges. Moreover, the above-stated zinc fines and/or KOH concentration may be implemented in a cell either alone or in combination with the inhibitors described herein (e.g., a phosphate surfactant and/or sulfonated surfactant).

[0048] For instance, referring now to Fig. 4, the service life of LR03 cells were tested and compared against a control cell having 4% fines added to the anode without an inhibitor. The control cell also included a concentration of 37% KOH. A first test cell included 4% zinc fines in combination with RM-510 inhibitor, while a second test cell included 8% zinc fines in combination with RM-510 inhibitor. A third test cell included the additives of the first test cell, but further included an oleic acid inhibitor. A fourth test cell included the additives of the second test cell, but further included an oleic inhibitor. All test cells included a concentration of 34%

KOH. The cell performance was measured as the amount of time that elapsed before a cell output voltage of .9V was measured.

[0049] The decreasing cell performance component associated with the addition of RM-510 overcame the increasing cell performance component associated with the decrease of KOH concentration, as the service life of the first test cell was slightly reduced compared to the control cell. However, the addition of 4% fines to the second test cell (for a total of 8%) in combination with a reduced KOH concentration overcame the disadvantages of RM-510 and produced a cell having a greater service life than the control cell. The third test cell, which was identical to the first test cell but for the addition of an oleic acid inhibitor, produced a service life greater than both the first and second test cells. The fourth test cell, which was identical to the second test cell but for the addition of an oleic acid inhibitor, produced a service life greater than all other test cells. Accordingly, a cell having added zinc fines may achieve improved performance over a comparable cell without zinc fines, and the performance may be further enhanced when an oleic acid inhibitor is added to the anode.

[0050] Fig. 5 illustrates the results of various ANSI tests performed on a control cell and a test cell. The control cell had a KOH concentration of 37% and less than 5% zinc fines commonly present in the anode. The test cell had a KOH concentration of 34% and 8% zinc fines added to the anode. Both cells included a phosphate surfactant to suppress gassing. The separator was pre-wetted with 37% KOH concentration electrolyte for both cells. Both cells were tested at 1 A continuous, 1 A pulsed, 3.9 ohms at 1 hour/day, 250 mA at 1 hour/day, 10 ohm at 1 hour/day, and 43 ohm at 4 hours/day. In all cases, the test cell performed better than the control cell, thereby indicating that the reduction of KOH concentration from 37% and the addition of zinc fines increased cell performance. Cell performance was determined based on the amount of time that had elapsed for the cell to reach specific discharge voltages depending on the test. For instance, 1V was used for 1A continuous discharge; .9V was used for 1A pulse, .8V was used for 3.9 ohm 1 hr/day, .9V was used for 10 ohm 1 hr/day, and .9V was used for 43 ohm 4 hr/day.

[0051] Fig. 6 illustrates that cell performance may be increased further by reducing the KOH concentration in electrolyte that is used to pre-wet the separator of the cell. In particular, a control cell and a test cell were tested under the conditions described above with reference to Fig. 5. The control cell and test cell both included 8% zinc fines, and 34% KOH concentration in the anode. The separator of the control cell was pre-wetted with electrolyte having a 37% KOH concentration, while the separator of the test cell was pre-wetted with electrolyte having a 34%

KOH concentration. The increased cell performance of the test cell may thus be attributed to the decreased KOH concentration used to pre-wet the separator. The present invention contemplates that a KOH concentration within the range of 20% and 40%, and more preferably 30%-40%, and more preferably still 33% and 38% used to pre-wet the separator will produce increased cell performance with decreasing KOH concentrations. A KOH concentration between 20% and 30%, and more preferably between 25% and 30% to pre-wet the separator may also increase cell performance. Cell performance is particularly increased when the cell is discharged intermittently or during a pulsed discharge, as excess water is available for the cathodic reaction, and hydroxide ions are thus replenished during the rest period of the cell to fuel the anodic reaction. Cell performance in Fig. 6 was determined based on the criteria discussed above with reference to Fig. 5.

[0052] While additional reaction sites at the anode tend to produce increased gassing, the addition of sulfonated or sulfated organic acid surfactant alone or in combination with an organic phosphate ester surfactant reduces the gassing, thereby increasing cell performance. Nevertheless, the skilled artisan appreciates that the present invention may include, either alone or in combination, the KOH concentrations described herein, the addition of zinc particles as described herein, and the addition of sulfonated or sulfated organic acid surfactant alone, or in combination with an organic phosphate ester surfactant, to the anode, to improve cell performance as described throughout this disclosure.

[0053] Fig. 7 illustrates the performance of an LR6 test cell having a KOH concentration of 34% in the anode gel, a separator pre-wetted with 34% KOH, and a mixture of RM-510 (at 12 ppm relative to the anode gel) and Witconate (at 125 ppm relative to the anode gel) added to the anode gel. The test cell was discharged, and its performance compared to a control cell having 34% KOH in the gel, and a separator pre-wetted with 34% KOH, but with no Witconate added to the gel. Both the test cell and the control cell included an anode having 8% zinc fines. The cell performance, as determined by the amount of time needed for the cell to output 0.9V during continuous discharge, was found to increase when the mixture of inhibitors was used with a reduced KOH concentration. Fig. 7 thus shows that the addition of sulfonated or sulfated organic acid surfactant in combination with the use of an organic phosphate ester surfactant suppresses what was previously thought to be adverse effects of a low KOH concentration on continuous discharge performance, without adversely affecting the intermittent and pulse discharge performance gains observed at low KOH concentrations, as shown in Fig. 6. The use of relatively

low concentrations of KOH in the anode and pre-wet solutions (within any of the above-stated ranges) improves performance at high and low intermittent discharge rates.

[0054] The invention has been described in connection with what are presently considered to be the most practical and preferred embodiments. However, the present invention has been presented by way of illustration and is not intended to be limited to the disclosed embodiments.

Accordingly, those skilled in the art will realize that the invention is intended to encompass all modifications and alternative arrangements included within the spirit and scope of the invention, as set forth by the appended claims.

CLAIMS

WE CLAIM:

1. A gelled anode mixture comprising a metal alloy powder, a gelling agent, an alkaline electrolyte having a hydroxide concentration less than 40%, and surfactant having the general formula $Y SO_x^-$.
2. A gelled anode mixture as claimed in Claim 1 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.
3. A gelled anode mixture as claimed in Claim 1 wherein the surfactant is a salt of a sulfated octadecanoic acid.
4. A gelled anode mixture as claimed in Claim 1 wherein the surfactant is a sodium salt of sulfated oleic acid.
5. A gelled anode mixture as claimed in Claim 1 wherein the surfactant is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.
6. A gelled anode mixture as claimed in Claim 1 further comprising an organic phosphate ester surfactant.
7. A gelled anode mixture as claimed in Claim 6 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.
8. A gelled anode mixture as claimed in Claim 6 wherein the organic phosphate ester surfactant is RM-510.

9. A gelled anode mixture as claimed in Claim 6 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

10. A gelled anode mixture as claimed in Claim 9 wherein the surfactant of Claim 1 is a salt of a sulfated octadecanoic acid.

11. A gelled anode mixture as claimed in Claim 9 wherein the surfactant of Claim 1 is a sodium salt of sulfated oleic acid.

12. A gelled anode mixture as claimed in Claim 9 wherein the surfactant of Claim 1 is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

13. A gelled anode mixture as claimed in Claim 12 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

14. A gelled anode mixture as claimed in Claim 13 wherein the organic phosphate ester surfactant is RM-510.

15. A gelled anode mixture as claimed in Claim 5 wherein the surfactant is present at a concentration ranging substantially between .001% and .06% relative to the gelled anode mixture.

16. A gelled anode mixture as claimed in Claim 15, wherein the surfactant is present at a concentration ranging substantially between .002% and .03% relative to the gelled anode mixture.

17. A gelled anode mixture as claimed in Claim 5, wherein the surfactant is present at a concentration ranging substantially between .0015% and .09% relative to the metal in the gelled anode mixture.

18. A gelled anode mixture as claimed in Claim 17, wherein the surfactant is present at a concentration ranging substantially between .003% and .045% relative to the metal in the gelled anode mixture.

19. A gelled anode mixture as claimed in Claim 6, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .02% relative to the gelled anode mixture..

20. A gelled anode mixture as claimed in Claim 19, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .005% relative to the gelled anode mixture.

21. A gelled anode mixture as claimed in Claim 6, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .02% relative to the metal in the gelled anode mixture.

22. A gelled anode mixture as claimed in Claim 21, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .0075% relative to the metal in the gelled anode mixture.

23. A gelled anode mixture as claimed in Claim 1, further comprising zinc particles of -140 mesh size.

24. A gelled anode mixture as claimed in Claim 23, wherein the zinc particles are present at a concentration less than 10% relative to the amount of metal in the mixture.

25. A gelled anode mixture as claimed in Claim 24, wherein the zinc particles are present at a concentration of between 4% and 8%.

26. A gelled anode mixture as claimed in Claim 24, wherein the zinc particles are present at a concentration of substantially 8%.

27. A gelled anode mixture as claimed in Claim 23, wherein the zinc particles are between +200 and -140 mesh size..

28. A gelled anode mixture as claimed in Claim 27, wherein the hydroxide concentration is between 20% and 30%.

29. A gelled anode mixture as claimed in 23, wherein the zinc particles comprise zinc fines between +625 and -200 mesh size.

30. A gelled anode mixture as claimed in Claim 29, wherein the hydroxide has a concentration between 30% and 40%.

31. A gelled anode mixture as claimed in Claim 23, wherein the zinc is a zinc alloy.

32. A gelled anode mixture as claimed in Claim 1, wherein the hydroxide concentration is substantially between 20% and 40%.

33. A gelled anode mixture as claimed in Claim 32, wherein the hydroxide concentration is substantially between 30% and 40%.

34. A gelled anode mixture as claimed in Claim 33, wherein the hydroxide concentration is substantially 34%.

35. A gelled anode mixture as claimed in Claim 1, wherein the hydroxide comprises KOH.

36. A gelled anode mixture comprising a metal alloy powder, a gelling agent, an alkaline electrolyte, zinc particles of -140 mesh size, and a surfactant having the general formula $Y SO_x^-$.

37. A gelled anode mixture as claimed in Claim 36 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

38. A gelled anode mixture as claimed in Claim 36 wherein the surfactant is a salt of a sulfated octadecanoic acid.

39. A gelled anode mixture as claimed in Claim 36 wherein the surfactant is a sodium salt of sulfated oleic acid.

40. A gelled anode mixture as claimed in Claim 36 wherein the surfactant is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

41. A gelled anode mixture as claimed in Claim 36 further comprising an organic phosphate ester surfactant.

42. A gelled anode mixture as claimed in Claim 41 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

43. A gelled anode mixture as claimed in Claim 41 wherein the organic phosphate ester surfactant is RM-510.

44. A gelled anode mixture as claimed in Claim 41 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

45. A gelled anode mixture as claimed in Claim 44 wherein the surfactant of Claim 33 is a salt of a sulfated octadecanoic acid.

46. A gelled anode mixture as claimed in Claim 44 wherein the surfactant of Claim 33 is a sodium salt of sulfated oleic acid.

47. A gelled anode mixture as claimed in Claim 44 wherein the surfactant of Claim 33 is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

48. A gelled anode mixture as claimed in Claim 47 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

49. A gelled anode mixture as claimed in Claim 48 wherein the organic phosphate ester surfactant is RM-510.

50. A gelled anode mixture as claimed in Claim 40 wherein the surfactant is present at a concentration ranging substantially between .001% and .06% relative to the gelled anode mixture.

51. A gelled anode mixture as claimed in Claim 50, wherein the surfactant is present at a concentration ranging substantially between .002% and .03% relative to the gelled anode mixture.

52. A gelled anode mixture as claimed in Claim 40, wherein the surfactant is present at a concentration ranging substantially between .0015% and .09% relative to the metal in the gelled anode mixture.

53. A gelled anode mixture as claimed in Claim 52, wherein the surfactant is present at a concentration ranging substantially between .003% and .045% relative to the metal in the gelled anode mixture.

54. A gelled anode mixture as claimed in Claim 41, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .02% relative to the gelled anode mixture..

55. A gelled anode mixture as claimed in Claim 54, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .005% relative to the gelled anode mixture.

56. A gelled anode mixture as claimed in Claim 41, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .02% relative to the metal in the gelled anode mixture.

57. A gelled anode mixture as claimed in Claim 56, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .0075% relative to the metal in the gelled anode mixture.

58. A gelled anode mixture as claimed in Claim 36, wherein the zinc particles are present at a concentration of less than 10 % relative to the gelled anode mixture.

59. A gelled anode mixture as claimed in Claim 58, wherein the zinc fines are present at a concentration of between 4% and 8% relative to the gelled anode mixture.
60. A gelled anode mixture as claimed in Claim 58, wherein the zinc fines are present at a concentration of substantially 8% relative to the gelled anode mixture.
61. A gelled anode mixture as claimed in Claim 36, wherein the zinc particles are between +200 and -140 mesh size.
62. A gelled anode mixture as claimed in Claim 61, further comprising a hydroxide having a concentration between 20 and 30%.
63. A gelled anode mixture as claimed in Claim 36, wherein the zinc particles comprise zinc fines of +625 and -200 mesh size.
64. A gelled anode mixture as claimed in Claim 36, wherein the zinc particles are present at a concentration of 1% and 10%.
65. A gelled anode mixture as claimed in Claim 36, wherein the electrolyte further comprising a hydroxide having a concentration between 20% and 40%.
66. A gelled anode mixture as claimed in Claim 65, wherein the hydroxide has a concentration between 30% and 40%.
67. A gelled anode mixture as claimed in Claim 65, wherein the hydroxide has a concentration between 20% and 30%.
68. A gelled anode mixture as claimed in Claim 65, wherein the hydroxide is KOH.
69. A gelled anode mixture as claimed in Claim 36, wherein the zinc particles include a zinc alloy.
70. A gelled anode mixture comprising a metal alloy powder, a gelling agent, an alkaline electrolyte having a hydroxide concentration less than 34%, and zinc particles of -140 mesh size.
71. A gelled anode mixture as claimed in Claim 70, wherein the zinc particles are between +200 and -140 mesh size.

72. A gelled anode mixture as claimed in Claim 70, wherein the hydroxide concentration is between 20% and 30%.

73. A gelled anode mixture as claimed in Claim 70, wherein the zinc particles comprise zinc fines between +625 and -200 mesh size.

74. A gelled anode mixture as claimed in Claim 73, wherein the hydroxide concentration is between 25% and 33%.

75. A gelled anode mixture as claimed in Claim 70, wherein the zinc particles comprise a zinc alloy.

76. A gelled anode mixture as claimed in Claim 70, further comprising a surfactant having the general formula $Y SO_x^-$.

77. A gelled anode mixture as claimed in Claim 76 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

78. A gelled anode mixture as claimed in Claim 76 wherein the surfactant is a salt of a sulfated octadecanoic acid.

79. A gelled anode mixture as claimed in Claim 76 wherein the surfactant is a sodium salt of sulfated oleic acid.

80. A gelled anode mixture as claimed in Claim 76 wherein the surfactant is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

81. A gelled anode mixture as claimed in Claim 76 further comprising an organic phosphate ester surfactant.

82. A gelled anode mixture as claimed in Claim 81 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

83. A gelled anode mixture as claimed in Claim 81 wherein the organic phosphate ester surfactant is RM-510.

84. A gelled anode mixture as claimed in Claim 81 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

85. A gelled anode mixture as claimed in Claim 84 wherein the surfactant of Claim 33 is a salt of a sulfated octadecanoic acid.

86. A gelled anode mixture as claimed in Claim 84 wherein the surfactant of Claim 33 is a sodium salt of sulfated oleic acid.

87. A gelled anode mixture as claimed in Claim 84 wherein the surfactant of Claim 33 is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

88. A gelled anode mixture as claimed in Claim 87 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

89. A gelled anode mixture as claimed in Claim 88 wherein the organic phosphate ester surfactant is RM-510.

90. An alkaline electrochemical cell comprising:
a positive current collector;
a cathode in contact with the positive current collector;
a gelled anode comprising a metal alloy powder, a gelling agent, an alkaline electrolyte having a hydroxide concentration less than substantially 40%, and a surfactant having the general formula $Y SO_x^-$;
a separator between the cathode and the anode; and
a negative current collector in electrical contact with the anode.

91. An alkaline electrochemical cell as claimed in Claim 90 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.
92. An alkaline electrochemical cell as claimed in Claim 90 wherein the surfactant is a salt of a sulfated octadecanoic acid.
93. An alkaline electrochemical cell as claimed in Claim 90 wherein the surfactant is a sodium salt of sulfated oleic acid.
94. An alkaline electrochemical cell as claimed in Claim 90 wherein the surfactant is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.
95. An alkaline electrochemical cell as claimed in Claim 90 further comprising an organic phosphate ester surfactant.
96. An alkaline electrochemical cell as claimed in Claim 95 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.
97. An alkaline electrochemical cell as claimed in Claim 95 wherein the organic phosphate ester surfactant is RM-510.
98. An alkaline electrochemical cell as claimed in Claim 95 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.
99. An alkaline electrochemical cell as claimed in Claim 98 wherein the surfactant of Claim 66 is a salt of a sulfated octadecanoic acid.
100. An alkaline electrochemical cell as claimed in Claim 98 wherein the surfactant of Claim 66 is a sodium salt of sulfated oleic acid.

101. An alkaline electrochemical cell as claimed in Claim 98 wherein the surfactant of Claim 66 is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

102. An alkaline electrochemical cell as claimed in Claim 101 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

103. An alkaline electrochemical cell as claimed in Claim 102 wherein the organic phosphate ester surfactant is RM-510.

104. An alkaline electrochemical cell as claimed in Claim 90 wherein the surfactant is present at a concentration ranging substantially between .001% and .06% relative to the gelled anode mixture.

105. An alkaline electrochemical cell as claimed in Claim 104, wherein the surfactant is present at a concentration ranging substantially between .002% and .03% relative to the gelled anode mixture.

106. An alkaline electrochemical cell as claimed in Claim 90, wherein the surfactant is present at a concentration ranging substantially between .0015% and .09% relative to the metal in the gelled anode mixture.

107. An alkaline electrochemical cell as claimed in Claim 106, wherein the surfactant is present at a concentration ranging substantially between .003% and .045% relative to the metal in the gelled anode mixture.

108. An alkaline electrochemical cell as claimed in Claim 95, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .02% relative to the gelled anode mixture..

109. An alkaline electrochemical cell as claimed in Claim 98, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .005% relative to the gelled anode mixture.

110. An alkaline electrochemical cell as claimed in Claim 95, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .02% relative to the metal in the gelled anode mixture.

111. An alkaline electrochemical cell as claimed in Claim 110, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .01% relative to the metal in the gelled anode mixture.

112. An alkaline electrochemical cell as claimed in Claim 90, further comprising zinc particles of -140 mesh size.

113. A gelled anode mixture as claimed in Claim 112, wherein the zinc particles are present at a concentration less than 10% relative to the amount of metal in the anode.

114. An alkaline electrochemical cell as claimed in Claim 113, wherein the zinc particles are present at a concentration of between 4% and 10% relative to the amount of metal in the anode.

115. An alkaline electrochemical cell as claimed in Claim 114, wherein the zinc particles are present at a concentration of substantially 8% relative to the amount of metal in the anode.

116. An alkaline electrochemical cell as claimed in Claim 112, wherein the zinc particles are between +200 and -140 mesh size.

117. An alkaline electrochemical cell as claimed in 116, wherein the hydroxide concentration is between 20 and 30%.

118. An alkaline electrochemical cell as claimed in Claim 112, wherein the zinc particles comprise zinc fines between +625 and -140 mesh size.

119. An alkaline electrochemical cell as claimed in Claim 118, wherein the hydroxide concentration is between 30% and 40%.

120. An alkaline electrochemical cell as claimed in Claim 90, wherein the hydroxide concentration is substantially between 20% and 40%.

121. An alkaline electrochemical cell as claimed in Claim 90, wherein the separator is pre-wetted with electrolyte having a hydroxide concentration between 30% and 40%.

122. An alkaline electrochemical cell as claimed in Claim 112, wherein the zinc particles comprise a zinc alloy.

123. An alkaline electrochemical cell comprising:
a positive current collector;
a cathode in contact with the positive current collector;
a gelled anode comprising a metal alloy powder, a gelling agent, an alkaline electrolyte, zinc particles having an average diameter less than 105 microns, and a surfactant having the general formula $Y SO_x^-$;
a separator between the cathode and the anode; and
a negative current collector in electrical contact with the anode.

124. An alkaline electrochemical cell as claimed in Claim 123 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

125. An alkaline electrochemical cell as claimed in Claim 123 wherein the surfactant is a salt of a sulfated octadecanoic acid.

126. An alkaline electrochemical cell as claimed in Claim 123 wherein the surfactant is a sodium salt of sulfated oleic acid.

127. An alkaline electrochemical cell as claimed in Claim 123 wherein the surfactant is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

128. An alkaline electrochemical cell as claimed in Claim 123 further comprising an organic phosphate ester surfactant.

129. An alkaline electrochemical cell as claimed in Claim 128 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

130. An alkaline electrochemical cell as claimed in Claim 128 wherein the organic phosphate ester surfactant is RM-510.

131. An alkaline electrochemical cell as claimed in Claim 128 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

132. An alkaline electrochemical cell as claimed in Claim 131 wherein the surfactant of Claim 99 is a salt of a sulfated octadecanoic acid.

133. An alkaline electrochemical cell as claimed in Claim 131 wherein the surfactant of Claim 99 is a sodium salt of sulfated oleic acid.

134. An alkaline electrochemical cell as claimed in Claim 131 wherein the surfactant of Claim 99 is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

135. An alkaline electrochemical cell as claimed in Claim 134 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

136. An alkaline electrochemical cell as claimed in Claim 135 wherein the organic phosphate ester surfactant is RM-510.

137. An alkaline electrochemical cell as claimed in Claim 123 wherein the surfactant is present at a concentration ranging substantially between .001% and .06% relative to the gelled anode mixture.

138. An alkaline electrochemical cell as claimed in Claim 137, wherein the surfactant is present at a concentration ranging substantially between .002% and .03% relative to the gelled anode mixture.

139. An alkaline electrochemical cell as claimed in Claim 123, wherein the surfactant is present at a concentration ranging substantially between .0015% and .09% relative to the metal in the gelled anode mixture.

140. An alkaline electrochemical cell as claimed in Claim 139, wherein the surfactant is present at a concentration ranging substantially between .003% and .045% relative to the metal in the gelled anode mixture.

141. An alkaline electrochemical cell as claimed in Claim 128, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .02% relative to the gelled anode mixture.

142. An alkaline electrochemical cell as claimed in Claim 145 wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0003% and .005% relative to the gelled anode mixture.

143. An alkaline electrochemical cell as claimed in Claim 128, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .02% relative to the metal in the gelled anode mixture.

144. An alkaline electrochemical cell as claimed in Claim 143, wherein the organic phosphate ester surfactant is present at a concentration ranging substantially between .0004% and .01% relative to the metal in the gelled anode mixture.

145. An alkaline electrochemical cell as claimed in Claim 123, wherein the zinc particles are present at a concentration of less than 10% relative to the metal in the anode.

146. An alkaline electrochemical cell as claimed in Claim 145, wherein the zinc particles are present at a concentration of between 4% and 8% relative to the gelled anode mixture.

147. An alkaline electrochemical cell as claimed in Claim 146, wherein the zinc particles are present at a concentration of substantially 8% relative to the gelled anode mixture.

148. An alkaline electrochemical cell as claimed in Claim 145, wherein the zinc particles are between +200 and -140 mesh size.

149. An alkaline electrochemical cell as claimed in 148, wherein the electrolyte has a hydroxide concentration between 20% and 30%.

150. An alkaline electrochemical cell as claimed in Claim 123, wherein the zinc particles comprise zinc fines between +625 and -200 mesh size.

151. An alkaline electrochemical cell as claimed in Claim 150, wherein the electrolyte comprises a hydroxide having a concentration substantially between 30% and 40%.

152. An alkaline electrochemical cell as claimed in Claim 123, wherein the electrolyte has a hydroxide concentration substantially between 20% and 40%.

153. An alkaline electrochemical cell as claimed in Claim 123, wherein the separator is pre-wetted with electrolyte having a hydroxide concentration between 30% and 40%.

154. An alkaline electrochemical cell as claimed in Claim 123, wherein the zinc particles comprise a zinc alloy.

155. An alkaline electrochemical cell comprising:
a positive current collector;
a cathode in contact with the positive current collector;
a gelled anode mixture comprising a metal alloy powder, a gelling agent, an alkaline electrolyte having a hydroxide concentration less than 34%, and zinc particles of -140 mesh size;
a separator between the cathode and the anode; and
a negative current collector in electrical contact with the anode.

156. An alkaline electrochemical cell as claimed in Claim 155, wherein the zinc particles are between +200 and -140 mesh size.

157. An alkaline electrochemical cell as claimed in Claim 156, wherein the hydroxide concentration is between 20% and 30%.

158. An alkaline electrochemical cell as claimed in Claim 155, wherein the zinc particles comprise zinc fines between +625 and -200 mesh size.

159. An alkaline electrochemical cell as claimed in Claim 155, wherein the hydroxide concentration is between 25% and 33%.

160. An alkaline electrochemical cell as claimed in Claim 155, wherein the hydroxide concentration is substantially 34%.

161. An alkaline electrochemical cell as claimed in Claim 155, wherein the zinc particles comprise a zinc alloy.

162. An alkaline electrochemical cell as claimed in Claim 155, wherein the hydroxide concentration is substantially between 20% and 30%.

163. An alkaline electrochemical cell as claimed in Claim 155, further comprising a surfactant having the general formula $Y SO_x^-$.

164. An alkaline electrochemical cell as claimed in Claim 163 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

165. An alkaline electrochemical cell as claimed in Claim 163 wherein the surfactant is a salt of a sulfated octadecanoic acid.

166. An alkaline electrochemical cell as claimed in Claim 163 wherein the surfactant is a sodium salt of sulfated oleic acid.

167. An alkaline electrochemical cell as claimed in Claim 163 wherein the surfactant is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

168. An alkaline electrochemical cell as claimed in Claim 163 further comprising an organic phosphate ester surfactant.

169. An alkaline electrochemical cell as claimed in Claim 168 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

170. An alkaline electrochemical cell as claimed in Claim 168 wherein the organic phosphate ester surfactant is RM-510.

171. An alkaline electrochemical cell as claimed in Claim 168 wherein Y is selected from the group consisting of an alkyl group, an aryl group, an alkylaryl group, a carboxy acid group, and a salt of any of the foregoing.

172. An alkaline electrochemical cell as claimed in Claim 171 wherein the surfactant of Claim 33 is a salt of a sulfated octadecanoic acid.

173. An alkaline electrochemical cell as claimed in Claim 171 wherein the surfactant of Claim 33 is a sodium salt of sulfated oleic acid.


174. An alkaline electrochemical cell as claimed in Claim 171 wherein the surfactant of Claim 33 is selected from the group consisting of Witconate™ 1840X, Dyasulf 2031, Dymosol 2031, Freedom SOA-70, and Freedom SOA-70WV.

175. An alkaline electrochemical cell as claimed in Claim 174 wherein the organic phosphate ester surfactant is an ethylene oxide-adduct type organic phosphate ester.

176. An alkaline electrochemical cell as claimed in Claim 175 wherein the organic phosphate ester surfactant is RM-510.


1 / 7

FIG. 1A




2 / 7

FIG. 1B



3 / 7

FIG. 1C







FIG. 2



5 / 7




FIG. 3

6 / 7




FIG. 5




FIG. 6

7 / 7




FIG. 7

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
4 September 2003 (04.09.2003)

PCT

(10) International Publication Number
WO 2003/073530 A3

- (51) International Patent Classification⁷: **H01M 4/62**
- (21) International Application Number:
PCT/US2003/005895
- (22) International Filing Date: 27 February 2003 (27.02.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/090,137 27 February 2002 (27.02.2002) US
- (71) Applicant: **RAYOVAC CORPORATION** [US/US]; 601 Rayovac Drive, Madison, WI 53744-4960 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- (72) Inventors: **ARMACANQUI, Miguel, E.**; 4322 Critchell Terrace, Madison, WI 53711 (US). **NDZEBET, Ernest**; 8501 Old Sauk Road, Apt. 228, Middleton, WI 53562 (US). **BUSHONG, William, C.**; 6306 Keelson Drive, Madison, WI 53705 (US). **MOY, Gregory, S.**; 5301 Shawano Terrace, Madison, WI 53705 (US). **VU, Viet, H.**; 3926 Meridian Circle, Verona, WI 53593 (US). **MIHARA, David, R.**; 5 San Antonio Court, Madison, WI 53719 (US). **POIRIER, Jeffrey, A.**; 225 Carillon Drive, Madison, WI 53705 (US).
- (74) Agent: **FORMAN, Adam, J.**; Quarles & Brady LLP, 411 East Wisconsin Avenue, Milwaukee, WI 53202 (US).
- Published:**
— with international search report
— before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments
- (88) Date of publication of the international search report:
22 January 2004
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: ALKALINE CELL WITH PERFORMANCE ENHANCING ADDITIVES

(57) Abstract: A sulfonic acid type organic surfactant is incorporated into the gelled anode mixture of an alkaline electrochemical cell, optionally with an organic phosphate ester surfactant. Zinc fines may also be incorporated into the anode. The electrolyte included in the anode mixture may have a reduced hydroxide concentration. When a cell is provided whose anode mixture includes the two surfactants and zinc fines alone or in combination with a lowered hydroxide concentration in the electrolyte, discharge leakage is reduced and gel gassing is suppressed relative to that of gels lacking both surfactants. Additionally, cell discharge performance is improved relative to that of cells lacking both the zinc fines and lowered hydroxide concentration.

WO 2003/073530 A3

INTERNATIONAL SEARCH REPORT

International Application No

PC 03/05895

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01M4/62

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 H01M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 040 088 A (EKERN RONALD J ET AL) 21 March 2000 (2000-03-21) cited in the application	1,2, 32-35, 90,91, 120,121
A	column 4, lines 14-67	3-31, 36-89, 92-119, 122
Y	EP 0 510 239 A (MATSUSHITA ELECTRIC IND CO LTD) 28 October 1992 (1992-10-28) page 3, lines 17-24; example 5; table 5 ----- -/--	1,2, 32-35, 90,91, 120,121

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

5 September 2003

Date of mailing of the international search report

21.11.03

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Hammerstein, G.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 03/05895

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5 378 559 A (RANDELL CHRISTOPHER F ET AL) 3 January 1995 (1995-01-03) cited in the application claim 1 -----	6,7,13, 14,95, 96,102, 103
A	US 4 195 120 A (PRZYBYLA FRANCISZEK J ET AL) 25 March 1980 (1980-03-25) cited in the application claim 1 -----	6,7,13, 14,95, 96,102, 103
A,P	US 2002/182509 A1 (TZENG GEORGE TZONG-CHYI) 5 December 2002 (2002-12-05) paragraphs [0032], [0033], [0035] - [0037] -----	1-35, 90-122
A	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 03, 27 February 1998 (1998-02-27) & JP 09 306501 A (SHIN KOBE ELECTRIC MACH CO LTD), 28 November 1997 (1997-11-28) abstract -----	

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US 03/05895

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☐ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☒ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

1-35, 90-122

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☐ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. claims: 1-35,90-122

Claims 1-35 and 90-122 concern a gelled anode mixture and an electrochemical cell comprising such mixture. The gelled anode mixture comprises:

- a) a metal (zinc) alloy powder,
- b) a gelling agent,
- c) an alkaline electrolyte,
- d) having a hydroxide concentration of less than 40 %,
- e) a surfactant YSOx.

2. claims: 36-69,123-154

Claims 36-69 and 123 -154 concern a gelled anode mixture and an electrochemical cell comprising such mixture. The gelled anode mixture comprises:

- a) a metal (zinc) alloy powder,
- b) a gelling agent,
- c) an alkaline electrolyte,
- e) a surfactant YSOx,
- f) zinc particles of -140 mesh/105 um size.

3. claims: 70-89,155-176

Claims 70-89 and 155-176 concern a gelled anode mixture and an electrochemical cell comprising such mixture. The gelled anode mixture comprises:

- a) a metal (zinc) alloy powder,
- b) a gelling agent,
- c) an alkaline electrolyte,
- d) having a hydroxide concentration of less than 34 %,
- f) zinc particles of -140 mesh size.

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PC 03/05895

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 6040088	A	21-03-2000	NONE	
EP 0510239	A	28-10-1992	JP 2006822 C JP 4322060 A JP 7038306 B AU 620280 B1 CA 2042527 A1 DE 69127190 D1 DE 69127190 T2 EP 0510239 A1 KR 9502957 B1 US 5128222 A	11-01-1996 12-11-1992 26-04-1995 13-02-1992 23-10-1992 11-09-1997 19-02-1998 28-10-1992 28-03-1995 07-07-1992
US 5378559	A	03-01-1995	NONE	
US 4195120	A	25-03-1980	AR 223855 A1 AU 530178 B2 AU 5201779 A BE 879750 A1 BR 7907045 A CA 1138031 A1 CS 216811 B2 DD 160205 A5 DE 2943072 A1 DK 464879 A ES 8100554 A1 FR 2441277 A1 GB 2033140 A ,B HK 19588 A IE 49203 B1 IL 58435 A IT 1126308 B JP 1762712 C JP 2031461 B JP 55069969 A MX 152661 A NL 7907979 A NO 793528 A ,B, PL 219408 A1 SE 7909068 A ZA 7905885 A	30-09-1981 07-07-1983 08-05-1980 15-02-1980 09-09-1980 21-12-1982 26-11-1982 11-05-1983 14-05-1980 04-05-1980 16-01-1981 06-06-1980 14-05-1980 25-03-1988 21-08-1985 30-07-1982 21-05-1986 28-05-1993 13-07-1990 27-05-1980 07-10-1985 07-05-1980 06-05-1980 11-08-1980 04-05-1980 26-11-1980
US 2002182509	A1	05-12-2002	WO 02099912 A2 US 2002160247 A1	12-12-2002 31-10-2002
JP 09306501	A	28-11-1997	NONE	

Form PCT/SA/210 (patent family annex) (July 1992)